

Physical and Mechanical Properties Test Report

COLUMBIA		Compound	Fluorocarbon, 75 duro		
		Customer:	Pave Technology		
		Material Spec:	ASTM D2000 M2HK810 A1-10 B38 EF31 EO78 EO88 Z1 Z1=DURO 75±5 Shore A		
Test Item		Unit	Spec.	Value	Test Method
Original Properties	Hardness Shore A	Point	75±5	77	ASTM D2440
	Tensile Strength	Psi	1450	2137	ASTM D412
	Elongation	%	150 Min	242	
Compression Set 200°C x 22h		%	50 Max	11.0	ASTM D395B
Heat Aged Properties 250°C x 70h	Hardness Change Shore A	Point	10 Max	3	ASTM D573
	Tensile Change	%	-25 Max	-16	
	Elongation Change	%	-25 Max	-4	
Fluid Resistance Fuel C 23°C x 70h	Hardness Change Shore A	Point	±5	-3	ASTM D471
	Elongation Change	%	-20 Max	-13	
	Tensile Change	%	-25 Max	-21	
	Volume Change	%	0/10	5	
Fluid Resistance Service Fluid 101 200°C x 70h	Hardness Change Shore A	Point	-15/5	-11	ASTM D471
	Elongation Change	%	-20 Max	-9	
	Tensile Change	%	-40 Max	-26	
	Volume Change	%	0/15	14	

Testing data on file

Checked by:

Carolyn Gilden
Quality Technician

NOTICE TO CUSTOMERS: All information contained in this report is based on ASTM or other standards which may or may not apply to actual user conditions. The information in this report is based on typical test data. It is intended for use by technically skilled individuals, to use at their own discretion and risk. Since the values are typical values, they should not be used as specifications. Since conditions of actual or intended use are outside our knowledge or control, we make no warranties, expressed or implied, and assume no liability in connection with any use of this information, nor do we make any claims or statements about the fitness of our product for use in any specific application or for any particular purpose. It is the customers sole responsibility to test the materials specified to assure satisfactory performance in the intended application. The data in this report is subject to change or correction at any time without notice.